



Product information sheet

GalerieArt™ gloss

Coated fine paper available in sheets and reels for offset printing

Technical specifications

PARAMETER	STANDARD	UNIT	90	100	115	130	135	150	170	200	250	300	350	400
BASIS WEIGHT	ISO 536	g/m ²	90	100	115	130	135	150	170	200	250	300	350	400
BRIGHTNESS (illuminant D65/10°)	ISO 2470-2	%	99	99	99	99	99	99	99	99	99	99	99	99
CIE WHITENESS (D65/10°)	ISO 11475	%	124	125	126	126	126	126	126	126	126	126	126	126
OPACITY	ISO 2471	%	90	92	93,5	94,5	95	96	97	98	98,5	99	99,5	99,5
GLOSS TAPPI 75°	ISO 8254-1	%	66	66	64	64	64	64	64	64	66	66	66	66
ROUGHNESS PPS	ISO 8791-4	µm	0,8	0,8	0,8	0,8	0,8	0,8	0,8	0,8	0,7	0,8	0,8	0,9
THICKNESS	ISO 534	µm	66	74	85	94	97	110	128	152	190	234	280	328
BULK	ISO 534	cm ³ /g	0,73	0,74	0,74	0,72	0,72	0,73	0,75	0,76	0,76	0,78	0,80	0,82
RELATIVE HUMIDITY (23°C)	TAPPI 502	%	50	50	50	50	50	50	50	50	50	50	50	50

Print recommendations

Dot area	For dot areas over 320% we recommend Under Colour Removal (UCR).
Processing	Allow paper time to acclimatise to press room conditions before removing outer packaging. Strapping bands (if applied) should be removed shortly after delivery. Outer wrappers should be removed only when ready to print. Ideal press room conditions should be 50% ± 5 % relative humidity at 20°C.
Finishing	Suitable for all standard finishes, foil laminating (>130gsm), embossing and die cutting. Varnishes include: dispersion, print, UV, spot, relief, iriodin, scented & acqueous.
Converting	Pre-creasing before folding is recommended from 135 um thickness onwards. Crease channel width should be a minimum of 2x paper thickness plus thickness creasing knife (plus or minus 0,2 mm). Crease channel depth should ± 1.5x paper thickness. Creasing knife 2 point (0,71 mm) (this and that depending on your crease/fold device).
Assisted drying methods	When using infra red drying methods, stack temperature should not exceed 37°C. Suitable for UV cure inks.

Mill certifications

- The environmental performance is monitored and continuously improved according to the requirements of Eco-Management and Audit Scheme (EMAS).
- The quality of the manufacturing is managed according to the requirements of ISO 9001.
- The environmental aspects of the mill are managed according to the requirements of ISO 14001.
- The energy consumed and the emissions generated by the mill are managed according to ISO 50001.
- All fibers from sustainability and controlled sources. FSC® may have limited availability, please check with your local sales office.
- All fibers from sustainability and controlled sources. PEFC™ may have limited availability, please check with your local sales office.
- The health and safety of the mill employees are managed according to the requirements of OHSAS 18001.

Target production values
Regional variations in specifications may apply; please contact your local Sales office for more information.
Updated : 08.06.2016

Product certifications

- All fibers from sustainable and controlled sources. PEFC™ may have limited availability, please check with your local sales office.
- All fibers from sustainable and controlled sources. FSC® may have limited availability, please check with your local sales office.
- Pulp is bleached without the use of chlorine (ECF).
- Meets the purity requirements (heavy metal content) of EN 71-3 'Toy Safety', part 3 'Migration of certain elements' and part 9 'Organic chemical compounds'.
- The key environmental parameters of the product are presented at the Paper Profile.
- Archivability tested according to the requirements of DIN 6738, Lifespan class - LDK 24-85.
- Only approved chemicals used, in compliance with BfR recommendation XXXVI 'Paper and Board for Food Contact'. GalerieArt gloss is suitable for direct contact with dry and fatty foodstuff.
- Suitable for dry toner.

Packaging of product complies with packaging and waste directive 94/62/EC (article 11). GalerieArt gloss is fully recyclable.





Product information sheet

GalerieArt™ silk

Coated fine paper available in sheets and reels for offset printing

Technical specifications

PARAMETER	STANDARD	UNIT	90	100	115	130	135	150	170	200	250	300	350	400
BASIS WEIGHT	ISO 536	g/m ²	90	100	115	130	135	150	170	200	250	300	350	400
BRIGHTNESS (illuminant D65/10°)	ISO 2470-2	%	100	100	100	100	100	100	100	100	100	100	100	100
CIE WHITENESS (D65/10°)	ISO 11475	%	127	127	127	127	127	127	127	127	127	127	127	127
OPACITY	ISO 2471	%	91	92,5	94,5	95	95,5	96,5	97,5	98	98,5	99	99,5	99,5
GLOSS TAPPI 75°	ISO 8254-1	%	37	37	37	37	37	37	37	37	37	37	37	37
ROUGHNESS PPS	ISO 8791-4	µm	1,5	1,5	1,5	1,5	1,5	1,5	1,5	1,5	1,6	1,8	2,0	2,1
THICKNESS	ISO 534	µm	76	84	97	109	113	126	145	172	230	288	353	420
BULK	ISO 534	cm ³ /g	0,84	0,84	0,84	0,84	0,84	0,84	0,85	0,86	0,92	0,96	1,01	1,05
RELATIVE HUMIDITY (23°C)	TAPPI 502	%	50	50	50	50	50	50	50	50	50	50	50	50

Print recommendations

Dot area	For dot areas over 320% we recommend Under Colour Removal (UCR).
Processing	Allow paper time to acclimatise to press room conditions before removing outer packaging. Strapping bands (if applied) should be removed shortly after delivery. Outer wrappers should be removed only when ready to print. Ideal press room conditions should be 50% ± 5 % relative humidity at 20°C.
Finishing	Suitable for all standard finishes, foil laminating (>130gsm), embossing and die cutting. Varnishes include: dispersion, print, UV (primer recommended), iriodin, scented & aqueous.
Converting	Pre-creasing before folding is recommended from 135 um thickness onwards. Crease channel width should be a minimum of 2x paper thickness plus thickness creasing knife (plus or minus 0,2 mm). Crease channel depth should ± 1.5x paper thickness. Creasing knife 2 point (0,71 mm) (this and that depending on your crease/fold device).
Assisted drying methods	When using infra red drying methods, stack temperature should not exceed 37°C. Suitable for UV cure inks.

Mill certifications

- EMAS** The environmental performance is monitored and continuously improved according to the requirements of Eco-Management and Audit Scheme (EMAS).
- ISO 9001** The quality of the manufacturing is managed according to the requirements of ISO 9001.
- ISO 14001** The environmental aspects of the mill are managed according to the requirements of ISO 14001.
- ISO 50001** The energy consumed and the emissions generated by the mill are managed according to ISO 50001.
- FSC® CoC** All fibers from sustainability and controlled sources. FSC® may have limited availability, please check with your local sales office.
- PEFC™ CoC** All fibers from sustainability and controlled sources. PEFC™ may have limited availability, please check with your local sales office.
- OHSAS 18001** The health and safety of the mill employees are managed according to the requirements of OHSAS 18001.

Target production values
Regional variations in specifications may apply; please contact your local Sales office for more information.
Updated : 08.06.2016

Product certifications

- PEFC™ credit material** All fibers from sustainable and controlled sources. PEFC™ may have limited availability, please check with your local sales office.
- FSC® Mix** All fibers from sustainable and controlled sources. FSC® may have limited availability, please check with your local sales office.
- ECF** Pulp is bleached without the use of chlorine (ECF).
- TOY-SAFETY** Meets the purity requirements (heavy metal content) of EN 71-3 'Toy Safety', part 3 'Migration of certain elements' and part 9 'Organic chemical compounds'.
- PROFILE** The key environmental parameters of the product are presented at the Paper Profile.
- ARCHIVING** Archivability tested according to the requirements of DIN 6738, Lifespan class - LDK 24-85.
- Food Contact** Only approved chemicals used, in compliance with BfR recommendation XXXVI 'Paper and Board for Food Contact'. GalerieArt silk is suitable for direct contact with dry and fatty foodstuff.
- Dry toner suitable** Suitable for dry toner.

Packaging of product complies with packaging and waste directive 94/62/EC (article 11). GalerieArt silk is fully recyclable.

